

Börresen Cooltech AS Postboks 130 Holmlia 1203 Oslo Norway	Your order 35775	
	Our reference 113010	Packing slip / Date PS515438 15.1.2016
	Your reference Lasse Djupvik	

Item	Product , Grade and Size			
001	Cupori 210 Ref kopparrör EN 12735-1 Cu-DHP R290 53,98(2 1/8)X1,78 MM X 5 M Nitrogenfyllda	548.10	Kg	PU113010.1
		210.00	M	
003	Cupori 210 Ref kopparrör EN 12735-1 Cu-DHP R290 12,7 (1/2)X0,89 MM X 5 M Nitrogenfyllda	549.07	Kg	PU113010.3
		1860.00	M	
004	Cupori 210 Ref kopparrör EN 12735-1 Cu-DHP R290 19,05 (3/4)X1,07 MM X 5 M Nitrogenfyllda	551.11	Kg	PU113010.4
		1020.00	M	
005	Cupori 210 Ref kopparrör EN 12735-1 Cu-DHP R290 22,23 (7/8)X1,14 X 5 M Nitrogenfyllda	550.29	Kg	PU113010.5
		815.00	M	

According to: EN 12735-1

Mechanical properties

Item	Tensile strength R _m N/mm ²	0.2 % proof strength R _{p0.2} N/mm ²	Elongation %	Hardness	Grain size mm
001	375	369	A5	6	
003	467	441	A5	6	
004	453	419	A5	7	
005	463	436	A5	7	

Chemical composition %

Cu-DHP/CW024A
 Cu min 99,90
 P 0,03

EDDY CURRENT TESTED:100%

Electrical conductivity at 20 ° C % IACS (mass), annealed

We hereby certify, that the material described above complies with the order.



Katja Silvanto

This document has been printed out through electrical mail.
 A copy with original signature is available in our factory.

These products have been produced under a certified Quality System
 ISO 9001: 2008 / DNV Certificate No.80561-2010-AQ-FIN-FINAS

Cupori Oy

P.O. Box 60, FIN-28101, Pori, Finland
 Tel. +358 2 511 4111, Fax +358 2 511 4002
 Domicile: Pori, Finland. Business ID 2639859-8, VAT FI26398598

Börresen Cooltech AS Postboks 130 Holmlia 1203 Oslo Norway	Your order 35775	
	Our reference 113010	Packing slip / Date PS515438 15.1.2016
	Your reference Lasse Djupvik	

Item	Product, Grade and Size			
006	Cupori 210 Ref kopparrör EN 12735-1 Cu-DHP R290 28,58 (1 1/8)X 1,27 MM X 5 M Nitrogenfylda	550.37	Kg	PU113010.6
		565.00	M	
007	Cupori 210 Ref kopparrör EN 12735-1 Cu-DHP R290 34,93(1 3/8)X1,4 MM X 5 M Nitrogenfylda	514.02	Kg	PU113010.7
		390.00	M	

According to: EN 12735-1

Mechanical properties

Item	Tensile strength R _m N/mm ²	0.2 % proof strength R _{p0.2} N/mm ²	Elongation %	Hardness	Grain size mm
006	452	417	A5	6	
007	450	434	A5	5	

Chemical composition %

Cu-DHP/CW024A

Cu min 99,90

P 0,03

EDDY CURRENT TESTED:100%

Electrical conductivity at 20 ° C % IACS (mass), annealed

We hereby certify, that the material described above complies with the order.



Katja Silvanto

This document has been printed out through electrical mail.
 A copy with original signature is available in our factory.

These products have been produced under a certified Quality System
 ISO 9001: 2008 / DNV Certificate No.80561-2010-AQ-FIN-FINAS

Cupori Oy

P.O. Box 60, FIN-28101, Pori, Finland
 Tel. +358 2 511 4111, Fax +358 2 511 4002
 Domicile: Pori, Finland. Business ID 2639859-8, VAT FI26398598